

# **ABIC TESTING LABORATORIES, INC.**

24 Spielman Road  
Fairfield, NJ 07004

973-227-7060  
Fax: 973-227-0172

To: Asphalt Art USA  
Mr. Steve Blackowicz

February 22, 2012

From: Leonard Mackowiak

Subject: Static Coefficient Of Friction Testing  
Project No 5390-02

## **Introduction**

ABIC Testing Laboratories, Inc. was authorized to test the following samples for static coefficient of friction (SCOF). The coefficient of friction determination was made using the James Machine as specified in ASTM D-2047. Testing was conducted using dry leather.

- CatWalk
- ClearWalk
- SportWalk

## **Results**

| <u>Test Product</u> | <u>Coefficient Of Friction Values(SCOF)</u>                    | <u>Average(SCOF)</u> |
|---------------------|--|----------------------|
| ClearWalk           | .71, .68, .70, .64, .67, .70, .67, .70,<br>.67, .67, .70, .68A | .68                  |
| CatWalk             | .63, .65, .61, .64, .62, .61, .63, .59,<br>.60, .64, .62, .64  | .62                  |
| SportWalk           | .65, .60, .65, .63, .68, .64, .68, .67,<br>.63, .66, .63, .70  | .65                  |

## **Discussion**

It is generally recognized that a walking surface must have a static coefficient of friction of 0.5 or greater to be considered slip resistant. In our evaluation the Asphalt Art USA samples identified as ClearWalk, CatWalk and SportWalk meet this standard.

Respectfully submitted,



Leonard Mackowiak  
Vice President