

Jessup Griptape® Colors Sidewalk Gray 3350

Issue Date: 11/1/2015 Version 1.1

DESCRIPTION

Jessup Griptape® Colors Sideway Gray 3350 is a commercial grade aluminum oxide non-slip tape that has been designed to meet OSHA standards for general purpose anti-slip surface applications.

APPLICATION

Jessup Griptape® Colors Sideway Gray 3350 is designed for indoor and outdoor non-skid applications that require long-term anchorage to a wide variety of surfaces. It has been successfully used in a wide range of industries including OEM, Action Sports, Building Safety, etc. and is NFSI certified for “High Traction”.

PROPERTIES

| PHYSICAL PROPERTIES | TEST METHODS | AVERAGE RESULTS |
|----------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Thickness | PSTC - 133 - Substrate - Pressure Sensitive adhesive - Release Liner | 0.027 inch (0.685 mm) 0.002 inch (0.051 mm) 0.006 inch (0.152 mm) |
| Peel Adhesion to: - Stainless Steel - Powder coated surfaces * - Polyethylene | PSTC – 101 15 minute dwell 24 hour dwell 15 minute dwell 24 hour dwell 15 minute dwell 24 hour dwell | 60 oz/in (66 N/100 mm) 80 oz/in (88 N/100 mm) 60 oz/in (66 N/100 mm) 80 oz/in (88 N/100mm) 40 oz/in (44 N/100 mm) 50 oz/in (55 N/100 mm) |
| Shear Adhesion to: - Stainless Steel | PSTC – 107 1/2” x 1/2” x 1000g | 1 hour |
| Tack | PSTC - 6 Rolling Ball Tack | < 2 inches |

* Color and lot variances of coated surfaces including paints, powder coatings, lacquers, stains, and other treatments may vary the performance of the tape and should be evaluated for the compatibility of the tape to the specific surface.

PROPERTIES

| PHYSICAL PROPERTIES | TEST METHODS | AVERAGE RESULTS |
|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Coefficient of Friction (Kinetic) | ASTM D1894 Dry Rubber Wet Rubber Dry Leather Wet Leather | 1.1 1.1 0.9 1.1 |
| Service Temperature High | 14 days at 150°F | No visible effects |
| Low | 14 days at -20°F | No visible effects |
| CHEMICAL PROPERTIES | REAGENT | RECOMMENDATION |
| <u>Solvent Resistance</u> (Product laminated to stainless steel panel and allowed to condition for 24 hours at room temperature before testing. Sample was covered with reagent to the point that edges of product are also exposed to the reagent. The product is exposed to reagent for one hour at room temperature, then reagent is removed and product is immediately tested for scrape resistances, delaminating, and other visual effects.) | Water 10% Salt Water Bleach Trichloroethylene 25% Sulfuric Acid 1% Sodium Hydroxide Unleaded Gasoline Diesel Fuel Hydraulic Fluid 50% Antifreeze in water MEK Mineral Spirits 99% IPA | Recommended Recommended Intermittent Contact Only Not Recommended Not Recommended Recommended Not Recommended Intermittent Contact Only Recommended Recommended Not Recommended Intermittent Contact Only Intermittent Contact Only |

Note: While the data contained herein is believed to be reliable averages of the product's properties, the data should not be used for specification purposes. Jessup Manufacturing cannot guarantee colors due to the variation in ink lots, manufacturing processes, etc. Sample colors may also vary as the samples may be shipped from different bundles or lots. Customers who desire specific performance data should contact Jessup Manufacturing Company for further recommendations.

WARRANTY

The determination of the suitability of this product for any specific use is solely the responsibility of the user. No representations, guarantees or warranties of any kind are made to the accuracy or suitability of information in this document to any specific applications.